

# CX-32

**CONCRETE**  
SOLUTIONS

## SLOW

Mortar retardant



OUTDOOR



### DOSE

It is added into the mixing water. Dosification depends on the wished effect, temperature and the cement type. Recommended dose between 0.1% and 2% according to cement weight.

Do not add to the dry mix of concrete.

### FEATURES AND USE

- Delay mortars and concrete setting.
- It is compatible with almost all the additives.
- It increases the putting in work time.
- Corrosives free.
- Storage: 12 months into their original containers.



TEMPERATURE OF CONCRETE	THE PUTTING IN WORK TIME OF CONCRETE							
	3 HOURS	5 HOURS	7 HOURS	9 HOURS	12 HOURS	15 HOURS	18 HOURS	21 HOURS
+10°C	-	-	0.20%	0.30%	0.50%	0.70%	0.90%	1.00%
+15°C	-	0.10%	0.30%	0.40%	0.60%	0.80%	1.10%	1.50%
+20°C	0.10%	0.20%	0.40%	0.50%	0.80%	1.10%	1.40%	1.80%
+25°C	0.20%	0.30%	0.50%	0.60%	1.00%	1.50%	2.00%	-
+30°C	0.20%	0.40%	0.60%	0.80%	1.20%	2.00%	-	-
+40°C	0.50%	1.30%	2.00%	-	-	-	-	-



Pallet with 24 containers of 25 l



Pallet with 60 containers of 10 l



Pallet with 48 boxes of 2 x 5 l



Pallet with 36 boxes of 9 x 1 l



**Preparation**  
Ready to use



6.0 - 7.0



**Useful life**  
Unlimited



**Fire resistance**  
A2 - s1 - d0



**Tools cleaning**  
With water



**Density**  
1.26 g/ml