E-12

INTERIOR


**USES** 



Enlucite \* -

# **PASTE FINISHES PASTA**

Suitable for full thin layer plastering.





#### **INFORMATION ON DIRECTIVE 2004/42/CE**

CATEGORY i!, HIGH PERFORMANCE ONE COMPONENT WATER-BASED COATINGS

LIMIT: 140G/L COV (2007); 140g/I COV(2010) This product contains 2,15g/I COV max.

#### **RECOAT**

BY ALL TYPES OF NON-ELASTIC PAINTS ONCE COMPLETELY DRY


**CODE (EN 16566):** 


## G3S1V2W2A0C0R0





of buckets of 25 kg.









of 18 x 1 kg.



### Preparation Ready to use. Clean tools with water.

Gypsum, plaster, cement, synthetic paint.

**FEATURES & USES** 

Non-drip.

Excellent workability. Easy to smooth and sand.

Great covering power. Thin layer applicable. Great finesse finishes.



Storage: 12 months inside its original packing and kept free from damp and humidity.

Substrates must be healthy, dry, cohesive, absorbent, well adhered, clean and free of dust.

Performance in 1mm layer 1.50 - 1.60 Kg/m<sup>2</sup>/mm



7.0 - 8.0



### Maximum thickness per layer 1 mm

Does not mount or roll on the joints/splice.

Does not tear away when worked with iron.



> 12 Kg/cm2 on cement & paint.



Fire classification A2 - s1 - d0



**Useful life** Unlimited



Drying in 1mm thickness Cement: 8 - 10 hrs. Paint: 10 hrs. approx.



Maximum granulometry 100 micras