

R29

Revox®

## GRANIFLEX

Ready-to-use microfibre elastic putty for filling and sealing micro cracks, fissures and cracks subject to movement.



**INFORMATION ABOUT DIRECTIVE 2004/42/CE**  
CATEGORY i1, HIGH PERFORMANCE COMPONENT COATINGS,  
WATERBASED

Limit: 140 g/l VOC (2007); 140 g/l VOC (2010)  
This product contains max. 27,30 g/l VOC

### COVERING

FOR ALL TYPES OF CONVENTIONAL PAINT  
AFTER COMPLETE DRYING

**CLASSIFICATION ACCORDING  
TO STANDARD EN 16566**

**G3S3V2W2A0C0R0**

### SURFACES

Gypsum, plaster, laminated plasterboards, cement, laminated cement boards, brick, stone, wood, concrete, aerated concrete and semi-absorbent surfaces.

Surfaces must be sound, dry, cohesive, absorbent, well adhered, clean and free of dust.

### CHARACTERISTICS

- Microfibre printing.
- Textured product.
- Excellent thixotropy.
- High adherence.
- Smoothing without migration of fibre to the surface.
- Flexible.

### IDEAL FOR

- Filling and sealing cracks and fissures in walls, terraces, roofs and façades subject to movement.
- Filling expansion joints in façades.

### ON-SITE APPLICATION

#### SURFACE PREPARATION

The surface must be sound, clean and free of any trace of saltpetre, fungi, microorganisms, grease, release oils and, in general, any type of material that could make it difficult for the product to adhere to the surface.



# R29

Revovox®

## GRANIFLEX

### ON-SITE APPLICATION

#### CLEANING

If surfaces present traces of fungi, algae or other type of microorganisms, we first proceed to curative treatment with our **RX-526 CLEAN ENERGY**. Apply the product to the surface to be treated and after 5-10 minutes of action clean the surface using a pressurised water machine or with a hard bristle brush.

Then, once the surface is completely dry, **RX-524 CLEAN MICRO** should be applied until the surface is completely impregnated. This preventive treatment is very effective and prevents future presence of microorganisms.

If there are saltpetre stains on the surface to be treated, carry out an initial cleaning process with our **RX-523 CLEAN SAL**, applying the material and then scraping it with a hard bristle brush. After mechanically cleaning the surface, it will need to be rinsed with plenty of clean water in order to neutralise any **CLEAN SAL** residue that may remain on the surface.

Any grease or oil must be completely eliminated to allow the product to adhere correctly to the surface. Therefore, we recommend using **RX-527 CLEAN OIL** for correct and total elimination of these substances.

Powdery surfaces must be consolidated with a fixative (**FIJAPREN** line), since dust prevents adhesion between materials. Similarly, old surfaces made up of perished plaster or poorly adhered parts must be cleaned up: **restoring perished surfaces without prior restoration is totally inadvisable**. If there are holes in the surface, these should be scraped down and removed until a consistent surface is created, then a fixative (**FIJAPREN** line) should be applied to remove traces of dust. This consistent surface will usually be made of brick, cement, functional plaster or any other material, as long as it can support the weight and tension of the layers subsequently applied, without breaking up or having its structure altered.

If cracks are present these must be repaired, i.e. opened up and their interiors fixed using a fixative (**FIJAPREN** line), left to dry for at least 4 hours and then filled to the required level.

#### DIRECTIONS FOR USE

Ready-to-use material. Do not dilute.

For cavity filling, we recommend using a medium sized spatula that allows for good pressure inside the cavity. Where possible, ensure that the width of the spatula is slightly greater than the size of the cavity.

Finally, after drying, sand the surface and, if no imperfections are observed, apply a fixative and then paint the surface.

R29

Revox®

GRANIFLEX

TECHNICAL CHARACTERISTICS

Density	1.51 ± 0.07 g/ml
Maximum thickness per layer	10 mm
Maximum granulometry	1000 µm
pH	9.0 – 10.0
Tool cleaning	With water

Drying time in 1 mm layer on paint surfaces (*)	12 h
Fire classification	D - s2 - d0

(\*) Depends on the environmental conditions, the nature of the surface and the thickness of application.

PERFORMANCE	
grams of paste applied per lineal metre in 1cm width	75 - 85

ADHERENCES	
CEMENT	PAINT
> 11 kg/cm <sup>2</sup>	> 15 kg/cm <sup>2</sup>

INFORMATION ON DIRECTIVE 2004/42/EC - Category i1	
VOC LIMIT	VOC CONTENT
140 g/l (2007) - 140 g/l (2010)	27,30 g/l max.

INFORMATION OF INTEREST

The Revox range manufacturing process is controlled in batches, which allows traceability of any incident. The quality system used includes each article's design and production controls, both in terms of the raw materials used, guaranteeing uniform manufacturing, and the final item obtained. The use of ecotechnologies in our facilities' manufacturing processes allows for efficient work, without damaging the environment that surrounds us.

- Non-flammable product.
- Avoid the product coming into contact with skin and eyes.
- Smoking, eating and drinking must be prohibited in the application area.
- Comply with legislation on health and safety at work.
- Keep the product in a dry place, in original containers that are kept properly closed.
- Store the containers between 5°C and 35°C.
- Recommended storage time: 12 months from the date of manufacture in its original packaging and protected from moisture.

For further information on protective measures and first aid, please refer to the product's Safety Data Sheet.

R29

Revovox®

# GRANIFLEX

## COMMENTS

- For appropriate use and correct application of the product, it is essential to first read the technical data sheet.
- The data provided in this data sheet are for guidance only and should not be considered binding. The data has been obtained in normal laboratory conditions and on standardised surfaces, and can vary depending on the conditions in which they are applied (absorption of the surface, applied thickness, temperature, environmental humidity, etc.). The intervals displayed have been shaped by measurement history. Slight deviations from the ranges presented in this technical sheet, whether higher or lower, will be accepted according to internal technical criteria and will not result in a loss of quality or affect the performance of the final product, due, among other factors, to variations in measurement conditions and the uncertainty associated with the instruments used.
- The working conditions of the users are beyond our control.
- The product must not be used for purposes other than those specified. It is recommended that the recommendations for use be strictly followed.
- Do not exceed the maximum recommended application thickness per coat.
- It is essential that the status of the surfaces be assessed prior to each application.
- Do not apply on non-absorbent or extremely crystalline surfaces.
- Do not mix with any material, as it will not retain its technical characteristics.
- We do not recommend applying the product on aged, badly adhered paints.
- Application temperature: from 5°C to 35°C.
- Maximum relative humidity: 85%.
- The technical department of **ESTABLECIMIENTOS BAI XENS** states that the designs of recently launched new products are considered to be in an experimental phase until an annual history can be constituted. From then on, the newly designed product is considered to be fully consolidated in the market. In the meantime, **BAIXENS** reserves the right to adapt its variable specifications or working ranges according to technical criteria. The data subject to modification will be identified with an asterisk for easy identification. These may be recently created products and/or products in an experimental phase or improvements in our various ranges due to market needs and/or demands.
- We place a technical-commercial team at your disposal that will advise you on any doubts or queries.

## PACKAGING

FORMAT	5 Kg.	1 Kg.
UNIT/BOX	4	12
PALLETS	24 BOXES	44 BOXES



Internal code	R29NF1321A20
---------------	--------------


**BAIXENS**

baixens.com

*Testing the difference*

**BAIXENS ESPAÑA**  
 POL. IND. MONCARRA, S/N  
 46230 ALGINET (VALENCIA)  
 T.: 961.750.834  
 F.: 961.752.471

**BAIXENS FRANCE**  
 14, RUE DU PONT NEUF  
 75001 PARIS (FRANCE)  
 T.: 0.800.90.14.37  
 F.: 0.800.90.20.52

**BAIXENS ITALIA / BULOVA**  
 VIA PIETRO NENNI, 36  
 46019 CIGOGNARA - MANTOVA (ITALY)  
 T.: 0375/88181/790016 F.: 0375/88831  
 www.bulova-pennelli.com

**BAIXENS PORTUGAL / ARGATINTAS**  
 AVENIDA PORTAS DO MINHO, Nº 711  
 4760 - 706 RIBEIRÃO,  
 V.N. FAMILIÇÃO  
 T.: 252 910 030  
 www.argatintas.pt