

RX-800

Unijunta®

**1 Hr. 30' – 2 Hrs. SETTING**

Suitable for filling joints between plasterboard sheets.  
Quick setting.



INTERIOR

**COATED**

PBY ALL TYPES OF NON-ELASTIC PAINTS  
ONCE COMPLETELY DRY

CLASSIFICATION ACCORDING TO STANDARD  
UNE-EN 13963

**STANDARD 3 B****QUALITY LEVEL 4 (Q4)****USES**

Plasterboard sheets.  
Surfaces must be sound, dry, cohesive, absorbent, well adhered, clean and free of dust.

**FEATURES**

- Great finesse and quality finishes.
- Excellent workability.
- Easy to smooth and sand.
- Excellent adhesion.
- Great filling power.
- Quick setting.
- Quick setting in thin layer.
- Storage: 6 months inside its original packing and kept free from damp and humidity.

**IDEAL FOR**

- Filling joints between plasterboard sheets merging paper or fibre tape.
- Repairing small flaws such as lines, dents and scratches on plasterboard sheets.
- Thin layer complete rendering of the plasterboard sheets (Q4 finish).



Pallet of 66  
sacks of 15 kg.



Pallet of 35  
cases of 4 x 5 kg.

**Water for mixing**

0,45 litres of water per Kg of powder.

**Performance**

250 – 300 g/m<sup>2</sup>/mm



7.0 - 8.0

**Maximum thickness for joining**

10 mm

**Adhesion**

> 4 Kg/cm<sup>2</sup> on concrete slab

**Fire Classification**

A1

**Useful life**

1 H 30' approx.

**Drying Time in 1 mm thickness**

Plaster: 1 H 30' - 2 Hrs.

**Maximum Granulometry**

300 Microns