

RX-802

Unijunta®

12 Hr. SETTING

Suitable for filling joints between plasterboard sheets.  
Slow setting.



UNE13963  
3B LENTO

Q1-Q4

INTERIOR



COATED

BY ALL TYPES OF NON-ELASTIC PAINTS  
ONCE COMPLETELY DRY

CLASSIFICATION ACCORDING TO STANDARD  
UNE-EN 13963

SLOW 3 B

QUALITY LEVEL 4 (Q4)

## USES

Plasterboard sheets.

Surfaces must be sound, dry, cohesive, absorbent, well adhered, clean and free of dust.

## FEATURES

- Great finesse and quality finishes.
- Excellent workability.
- Easy to smooth and sand.
- Excellent adhesion.
- Great filling power.
- Slow setting.
- Quick setting in thin layer.
- Storage: 12 months inside its original packing and kept free from damp and humidity.

## IDEAL FOR

- Filling joints between plasterboard sheets merging paper or fibre tape.
- Repairing small flaws such as lines, dents and scratches on plasterboard sheets.
- Thin layer complete rendering of the plasterboard sheets (Q4 finish).



Pallet of 66 sacks of  
15 Kg.



Pallet of 35  
cases of 4 x 5 Kg.



### Water for mixing

0,45 – 0,48 litres of water per Kg of powder.



### Performance

200 – 250 g/m<sup>2</sup>/mm



6.5 - 7.5



### Maximum thickness for joining

10 mm.



### Adhesion

> 5 Kg/cm<sup>2</sup> on concrete



### Fire Classification

A1



### Useful life

12 Hrs approx.



### Drying Time in 1 mm thickness

Plaster: 2 – 3 Hrs.



### Maximum Granulometry

300 microns